

EVA

EVA for Foam Application

▶ E220F

● Description

E220F is EVA resin for crosslinked foam applications including mid-sole and in-sole of athletic shoes. This grade is designed to be processed in conventional kneading and rolling equipment for mixing and dispersing crosslinking agent and foaming agent.

● Characteristics

E220F offers good processability during compounding with various additives. Foamed products made of this grade provide excellent spilt tear resistance, superb tensile and elongation properties, and good compression set properties.

● Applications

- ▶ Athletic shoe mid-soles and in-soles, Sandals, Cushion padding

● Physical Properties

Properties	Test Method	Units	E220F
Melt Index (190°C/2.16 kg)	ASTM D 1238	g/10min	3.0
Density	ASTM D 1505	g/cm ³	0.944
VA Content	Hanwha Total	%	22
Tensile Strength at Break	ASTM D 638	kg/cm ²	290
Elongation at Break	ASTM D 638	%	800
Shore Hardness	ASTM D 2240	A scale	90
		D scale	35
Vicat Softening Point	ASTM D 1525	°C	55
Melting Point	Hanwha Total	°C	83
Brittleness Temp.	ASTM D 746	°C	< -70

Data performed by or on behalf of Hanwha Total

● Food Contact Application

- ▶ There may be some limitation to apply Hanwha Total E220F to the food packaging
- ▶ Thus, the verification on the suitability is necessary. In case you might need additional information, please contact Hanwha Total Polymer Technical Service Team.

● Other Information

The information in this document can be used for reference only, not to be construed as specification. Customers are responsible for determine whether our product and information is suitable for their particular purpose and for the compliance with related law.

HANWHA TOTAL assumes no obligation or liability for the information in this document.

● Contacts

▶ **Product Information & Technical Services**

103, Dokgot 2-ro, Daesan-eup, Seosan-si, Chungcheongnam-do,
Korea, 31900

TEL : 82-41-660-6190 FAX : 82-41-660-6189

Disclaimer

This document is copyright of Hanwha Total petrochemical Co., Ltd. Any and all information and the values in this document are typical properties for reference, not to be confused with, or regarded as specification. Customers are responsible for determining whether our products and information are suitable for their particular purpose and for ensuring that Customer's location and handling practices are in compliance with laws and regulations. HANWHA TOTAL assumes no obligation or liability for the information in this document. NO EXPRESS WARRANTIES ARE GIVEN EXCEPT FOR ANY APPLICABLE WRITTEN WARRANTIES SPECIFICALLY PROVIDED BY HANWHA TOTAL. ALL IMPLIED WARRANTIES INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. HANWHA TOTAL is entitled to alter, change or modify any of the content herein at any time without prior notice, but not under any duty to do so.